



TECHNICAL DATASHEET

PENOSIL Premium Fire Rated Gunfoam B1

Professional fire protection foam with low post-expansion for demanding users. Fire class meets the European standards EN 1366-4 and DIN 4102-1.

Rated in accordance with EN 13501-2:2007. Good resistance to moisture and mould. Fast curing. Great results at low temperatures.

Packed in an aerosol can, can be used with a foam gun, moisture-curing. Cured foam is a good temperature and sound insulator. The foam has very good adhesion properties. Adheres well to most construction materials, except Teflon, polyethylene and silicone surfaces. After curing does not resist UV- radiation and needs to be covered.

Field of application

Used for the installation of fire-proof doors, insulation of feedthroughs of pipes and cables, sealing and fixation of pipes as well as thermal insulation – any place where high fire-proofness is required.

Application conditions

Usage temperature between +5 °C and +30 °C, best results at +20 °C. Can temperature during application +10 °C to +25 °C, best results at +20 °C. The surfaces must be clean from dust, loose particles and oil. Cured foam can be painted with water-based paints.


Application instruction

Hold the foam can in upright position and turn the gun side by holding the gun handle with one hand and turn the can with the other hand. Make sure that the gun is not pointed to other persons when turning it. The can must not be screwed to the gun with the valve upside down or by turning the gun on the can. After fixing the gun, shake the can well at least 20 times. The foam output can be adjusted by gun trigger. A moistened substrate ensures faster curing and better result. At low temperatures foam can must be warmed before work in warm room or water. Temperature of room or water must not exceed 30°C.

Insulation Wholesalers Ltd

P.O Box 1826, Palmerston North, New Zealand. **M** : +64 021 927 038 **P**: +64 06 329 8065 **F**: +64 06 329 8064

www.insulationwholesalers.co.nz



Cleaning

Uncured foam can be cleaned from tools and surfaces with PENOSIL Premium Foam Cleaner. Cured foam can be removed mechanically after softening with PENOSIL Premium Foam Remover. Hands, clothes and foam gun can be cleaned from uncured foam with moistened PENOSIL Premium Cleaning Wipes.

Technical specification

Property	Unit	Value
Tack free time	minute	12–16
Cutting time (30 mm bead)	minute	30–40
Completely cured in joint (at +23 °C)	hour	up to 18
Completely cured in joint (at +5 °C)	hour	up to 24
Density	kg/m ³	25–30
Fire class of cured foam (DIN 4102-1)		B1

Volume decrease	%	non
Post-expansion	%	up to 30
Flash point of cured foam	°C	400
Tensile strength (BS 5241)	N/cm ²	8
Compression strength at 10% deformation (DIN 53421)	N/cm ²	2,5
Thermal conductivity	W/m ² K	0,034
Temperature resistance of cured foam	°C	long term: -50 to +90 short term: -65 to +130

The values specified were obtained at 23 °C and 50% relative humidity, unless otherwise specified. Fire-resistance is tested and rated in accordance with EN 13501-2/2007:

Joint depth, mm	100	100	100	100	200	200	200	200
Joint width, mm	40	30	20	10	40	30	20	10
El, min	45	45	60	60	120	120	150	180

Colour

Light pink.

Package

1000 ml aerosol can, content 750 ml, 12 cans in a box.

Insulation Wholesalers Ltd

P.O Box 1826, Palmerston North, New Zealand. **M** : +64 021 927 038 **P**: +64 06 329 8065 **F**: +64 06 329 8064

www.insulationwholesalers.co.nz



NEW ZEALAND OWNED – SUPPLYING NEW ZEALAND AND AUSTRALIAN MARKETS

Storage

The cans must be stored and transported in vertical position. Store in a cool and dry place at +5 °C to +30°C.

The foam cans must not be stored above +50 °C, in vicinity of heat sources or in direct sun light. Guaranteed storage time in unopened package 12 months.

Safety requirements

The product is flammable. Protect from overheating and keep away from ignitions sources. Avoid direct sunlight and do not smoke at work.

May cause sensitisation by inhalation and skin contact. Ensure sufficient ventilation during application. Wear safety glasses and gloves.

Keep out of the reach of children.

Cured foam can be handled without any danger to health.

Detailed safety information is available on safety data sheet (SDS).

Insulation Wholesalers Ltd

P.O Box 1826, Palmerston North, New Zealand. **M** : +64 021 927 038 **P**: +64 06 329 8065 **F**: +64 06 329 8064

www.insulationwholesalers.co.nz